

General Product Description

Docol 800DP dual-phase steels offer good formability for the production of safety details in cars. These steels undergo special heat treatment, producing mainly two phase structure. Ferrite that imparts unique forming properties represents one phase, and martensite that accounts for the strength represents the other phase. Bainite may be present as complementary phase.

Dimension Range

Cold rolled / UC: thickness 0.50-2.10 mm, width up to 1527 mm.

Cold rolled / GI, GA, ZA: thickness 0.80-2.50 mm, width up to 1460 mm.

Slit strip and cut to length sheets are available upon request.

Grade and coating specific restrictions on available dimensions may occur.

Mechanical Properties

	Standard	Coating	Test direction	Yield strength R _{p0.2} (MPa)	Tensile strength R _m (MPa)	Elongation A ₈₀ (min %)	n ₄₋₆ (min)	n _{10-20/Ag} (min)	BH ₂ (min MPa)	Min. inner bending radius for a 90° bend ⁴⁾
Docol CR 440Y780T-DP	VDA 239-100	UC	L	440 - 550	780 - 900	14	0.15 ³⁾	0.11	30	1.0 x t
	VDA 239-100	GI, GA, ZA*	L	440 - 550	780 - 900	14 ¹⁾	0.15	0.11	30	1.8 x t
Docol CR 450Y780T-DP	SSAB	UC	L	450 - 550	780 - 900	15	—	—	—	1.0 x t
Docol CR 390Y800T-DL	SSAB	UC	T	390 -	800 - 950	13	—	—	—	1.0 x t
Docol CR 500Y800T-DP	SSAB	UC	T	500 - 650	800 - 950	10 ²⁾	—	—	—	1.0 x t
Docol 800DPX	SSAB	GI, GA*	T	620 - 770	800 - 950	10	—	—	—	0.9 x t

* Available upon request.

¹⁾ For GA coatings the minimum elongation value is reduced by 2 units.

²⁾ Decreased minimum elongation values apply for product thickness t < 0.70 mm (minus 2 units).

³⁾ For UC material the n₄₋₆ value is reduced by 0.02 units.

⁴⁾ In some cases tight bending radius may cause micro-cracking of the coating in the bend area. Where design permits, users are encouraged to employ larger radius.

Chemical Composition (ladle analysis)

	Coating	C (max %)	Si (max %)	Mn (max %)	P (max %)	S (max %)	Al (%)	Nb+Ti (max %)	Cr+Mo (max %)	B (max %)	Cu (max %)
Docol CR 440Y780T-DP	UC	0.16	0.40	1.80	0.020	0.010	0.015 - 1.00	—	—	0.005	0.20
	GI, GA, ZA*	0.18	0.80	2.50	0.050	0.010	0.015 - 1.00	0.15	1.00	0.005	0.20
Docol CR 450Y780T-DP	UC	0.16	0.40	1.80	0.020	0.010	From 0.015	0.10	—	—	—
Docol CR 390Y800T-DL	UC	0.16	0.40	1.80	0.020	0.010	From 0.015	0.10	—	—	—
Docol CR 500Y800T-DP	UC	0.15	0.40	1.80	0.020	0.010	From 0.015	0.10	—	—	—
Docol 800DPX	GI, GA*	0.18	1.00	2.50	0.050	0.010	0.015 - 1.00	0.15	1	0.005	0.20

* Available upon request.

Tolerances

Cold rolled (UC): Tolerances in accordance to EN 10131.

Hot-dip galvanized (GI, GA, ZA): Tolerances in accordance to EN 10143.

Customized dimensional and shape tolerances are available upon request.

Coatings

The metal coating options for Docol products include:

Hot-dip zinc coating (GI) consists almost entirely of zinc (>99%). It is lead free, resulting in a small zinc spangle size. The coating provides good corrosion protection.

Galvannealed coating (GA) is a zinc-iron alloy coating having an iron content of approximately 10%. Galvannealed is produced by post-heat treatment in continuous hot-dip coating process. Galvannealed provides excellent resistance weldability and corrosion protection of painted products.

Galfan coating (ZA) is a zinc-aluminium alloy coating having the eutectic composition approximately of 95% Zn and 5% Al. Galfan is produced in continuous hot-dip coating process. Galfan has better anticorrosive and forming properties than conventional hot-dip zinc coating (GI).

Grade specific availability of metal coatings for Docol products is given in the Mechanical properties table (Coating).

Coating type	Coating class	Standard	Closest in EN 10346, informative	Coating mass per side, single spot test (g/m ²)	Thickness per side informative (µm)
GI	40/40	VDA 239-100	Z100	40 - 60	5.6 - 8.5
GI	50/50	VDA 239-100	–	50 - 70	7.0 - 9.9
GI	60/60	VDA 239-100	Z140	60 - 90	8.5 - 12.7
GI	70/70	VDA 239-100	–	70 - 100	9.9 - 14.1
GI	85/85	VDA 239-100	–	85 - 115	12.0 - 16.2
GI	115/115	VDA 239-100	Z275	115 - 155	16.2 - 21.8
GA	40/40	VDA 239-100	ZF100	40 - 60	5.6 - 8.5
GA	50/50	VDA 239-100	ZF120	50 - 80	7.0 - 11.3
ZA	95	EN 10346	ZA95	–	7.0 -
ZA	130	EN 10346	ZA130	–	10.0 -

Docol metal coated products are available with surface quality for unexposed applications.

In addition to these coating masses, OEM specific coatings are available upon request.

Surface Treatments

Uncoated (UC): available as oiled.

Hot-dip galvanized (GI, GA, ZA): available as oiled and/or chemically passivated.

All surface treatments are in accordance with RoHS directive (2011/65/EU) and do not contain Chromium VI (Cr⁶⁺). Surface treatments provide only temporary surface protection during transportation and storage. In order to avoid corrosion damages, care must be taken to keep the products dry during transportation and storage. If they become wet, they must be separated and situated so that they are dried quickly.

Fabrication and Other Recommendations

For information concerning fabrication, see SSAB's brochures on www.ssab.com or consult Tech Support.

Appropriate health and safety precautions must be taken when bending, welding, cutting, grinding or otherwise working on the products.

Contact Information

www.ssab.com/contact